HIGH PERFORMANCE

EVO CV	Chambray	Tangelo Baltic	Jetty Putty	Cyan Ram	Bluet
SILICA	Cumulus	Aqua	Surf Alfresco	Marigold	Quartz
TRIBECA CV	Cloud	Shell	Cascade	Lichen Airy	Griffin Hearth
SILICA LEATHER	Chambray	Shadow Madder	Hyacinth Juniper	Eucəlyptus	Pewter Ink
CANTER EPU		Summer White	Nimbus	Kiwi Green	Earth

Ballad

Quarry

Tango

Iron

Night allseating



Technical Information

Width/	Fiber Content	Weight	Abrasion	Light-	Approx.	CI.
Pattern	& Backing		Resistance	fastness	Repeats	Code
54" Canter EPU	100% EPU Polyurethane	1.72 lb./	1,000,000	200 Hours	N/A	W
🥠 🖉 🗮 🛧 🖪.	Polyester Backing	linear yard	Double Rubs	Class 4		Bleach Cleanable (4:1)
54″ EVO CV	100% Clean Vinyl/Phthalate Free	2.37 lb./	1,000,000	200 Hours	N/A	WS
🥠 🖉 🗮 🛧 🖪	Polyester Backing	linear yard	Double Rubs	Class 4		Bleach Cleanable (10:1)
54" Silica	100% Silicone	1.60 lb./	365,000	200 Hours	N/A	WS
🥠 🖉 🗮 🛧 🖪	Polyester Backing	linear yard	Double Rubs	Class 4.5		Bleach Cleanable (4:1)
54" Silica Leather	100% Silicone Polyester Backing	1.57 lb./ linear yard	210,000 Double Rubs	200 Hours Class 4	N/A	WS Bleach Cleanable (4:1)
54" Tribeca CV	100% Clean Vinyl/Phthalate Free	1.92 lb./	100,000	200 Hours	N/A	W
🥠 🖉 🗮 🤆 🖪	Polyester Backing	linear yard	Double Rubs	Class 4		Bleach Cleanable (10:1)

EXPLANATION OF ACT ICONS FOR UPHOLSTERY

Hire Retardancy

Flammability testing determined as fabric's resistance to burning.

PASSES California 117 2013

Colorfastness to Wet and Dry Crocking

Colorfastness to wet & dry crocking refers to the rubbing off of color from the fabric onto clothing, hands or other materials and can occur under wet or dry conditions.

PASSES AATCC 8-1974 Dry Crocking: Class 4 minimum; Wet Crocking: Class 3 minimum 🗮 Colorfastness to Light

Colorfastness to light is the degree to which fabric will retain its color when exposed to light.

PASSES AATCC 16A-1974 or AATCC 16E-1976; Class 4 minimum at 40 hours

NOTE: Class 4 minimum at 60 hours is recommended for direct sunlight exposure situations.

🖈 Physical Properties

3 physical property tests include: brush pill test to determine a fabric's pilling. Breaking/tensile strength is the ability of a fabric to withstand tension without breaking or tearing. Seam slippage is the pulling apart of fabrics at the seams.

PASSES Brush Pill ASTM D3511, 3-4 minimum Breaking Strength ASTM D3597-D1682-64 (1975) 50 lbs. minimum in warp & weft

Abrasion

Abrasion is the ability of a fabric to withstand damage from wear and rubbing. There is a general contract specification as well as heavy duty specification.

PASSES

(Heavy Duty) ASTM 3597 modified (#10 cotton duck); 30,000 double rubs Wyzenbeek Method or ASTM D4966 (with 21 oz. weight); 40,000 rubs Martindale Method

Cleaning Code Definitions

W Water-based foam or cleaner. WS Water-based cleaning agents or foam.

Manufacturer recommends using a damp warm cloth after cleaning with bleach solution or Virox 5 followed by a dry clean cloth.

Please visit manufacturer's website for cleaning guide at www.themomgroup.com

M O M E N T U M

TO VIEW OUR ENTIRE FABRIC COLLECTION, VISIT ALLSEATING.COM

QUESTIONS? Email us at marketing@allseating.com T 1 800 583 3502 F 1 800 272 9911

TORONTO 5800 Avebury Road, Unit 3 Mississauga, ON L5R 3M3 CHICAGO* 325 North Wells Street, Suite 210 Chicago, IL 60654

NEW YORK* 1140 Broadway, Suite 902 New York, NY 10001

